

**FIBRATED PLASTIC ROOF CEMENT
CONTAINING SHORT STUFF® POLYETHYLENE E380F**

The following formulation combines the excellent rheological properties of Attagel® 36 asphalt thickener with Emtal® 42 talc, which serves as a reinforcing filler. Low percentages of polyolefin fibers are added to provide a fibrated appearance and excellent reinforcing properties. These cements meet the performance standards as described in Federal Specification SS-C-153C and ASTM D-2822. A pre-gelling step is included to improve thickening when using a low-speed (7 rpm) Planetary Mixer.

**FIBRATED PLASTIC ROOF CEMENT
FORMULATION (WT%)**

Order of Addition: _____	4863-19-1P
Sohio Grade B Cutback.....	24.00
RD4540 Surfactant.....	0.83
Mix 2 minutes	
Attagel® 36 Thickener.....	6.00
Mix until completely gelled (5-10 minutes)	
Sohio Grade B Cutback.....	44.92
Mix until homogenous (5 minutes)	
MiniFIBERS' SHORT STUFF® Polyethylene E380F.....	1.25
Emtal® 42 Talc.....	23.00
Mix until homogenous (10 minutes)	

FIBRATED CUTBACK TYPICAL PROPERTIES

Ring & Ball Softening Point	167°F
Needle Penetration	35 @ 77°F
Cutback Solids	62%/wt.
Saybolt Furol Viscosity	120 sec. @ 122°F

Information in this bulletin is the best available to us and is believed to be correct. No warranty is expressed or implied regarding its accuracy on the use of the product. Nothing herein constitutes permission or recommendation to practice any invention covered by any patent without a license from the owner of the patent.