

**FIBERED SELF-LEVELING FLOOR  
CONTAINING SHORT STUFF® POLYETHYLENE E505F**

<b><u>MATERIALS:</u></b>	<b><u>Pounds</u></b>
Portland Cement Type 1,2.....	564.0
Fondu Cement.....	94.0
EZ Spred.....	50.0
Elotex 2320 Polymer.....	82.5
Calcium Carbonate Filler.....	600.0
Simpson SLF Admix.....	25.0
MiniFIBERS' SHORT STUFF® Polyethylene E505F.....	6.0
#30 Mesh Sand.....	<u>1400.0</u>
	2821.5

Mix to a uniform consistency for at least 20 minutes. Make sure fibers are evenly dispersed throughout the mixture.

Information in this bulletin is the best available to us and is believed to be correct. No warranty is expressed or implied regarding its accuracy on the use of the product. Nothing herein constitutes permission or recommendation to practice any invention covered by any patent without a license from the owner of the patent.