

Technical Data Sheet

NOMEX® ARAMID FIBERS

General Description: A manufactured fiber in which the fiber-forming substance is a long-chain synthetic polyamide in which 85% of the amide linkages are attached directly to two aromatic rings.

Standard Filament Sizes: 2.0 denier per filament (dpf)

Standard Cut Lengths: 7mm
Other lengths available upon request.

Shrinkage, : 2.0%

Breaking Tenacity: 4.45-5.35 gpd

Elongation at Break: 27 to 37%

Moisture Content: 12 to 24%

Moisture Regain: 4.5 to 7.5%

Specific Gravity (g/cm³): 1.38

Effect of Heat: Does not melt. Does not propagate flame. Decomposes at 700°F. At about 800°F, carbonizes and forms a tough char.

Chemical Reactivity: Unaffected by most acids, except for some strength loss after long exposure to hydrochloric, nitric, or sulfuric acids. Generally good resistance to alkalis. Unaffected by most bleaches and solvents, except for some strength loss from exposure to sodium chlorite.

Dispersion: Easily dispersed in aqueous and non-aqueous systems. Surface treatment to aid dispersion applied as required.

Packaging: Fiber is packaged in corrugated boxes with polyethylene liners. Custom packaging available upon request.