

Technical Data Sheet

**PHYSICAL PROPERTIES
FYBREL® SYNTHETIC FIBER
POPULAR PAPER MAKING GRADES**

TYPE	MELT POINT (°C)	PRODUCT CODE	CANADIAN STANDARD FREENESS (cc)	CLASSIFIED FIBER LENGTH (mm)	MOISTURE% (Average)	COARSENESS
E (Polyethylene)	135	E400	580	0.9	62	Standard
		EST-8	540	0.9	60	Standard
		E620	340	1.2	64	Standard
UL (Polyethylene)	125	UL410	600	1.0	55	Coarse
NL (Denatured PE)	100	NL490	720	1.0	55	Coarse
AU (Denatured PE)	125	AU690	680	1.2	55	Coarse
Y (Polypropylene)	165	Y600	720	1.0	6.0	Very Coarse