

## **Technical Data Sheet**

NYLON FIBERS

Type 6,6 Bright High Tenacity

Product Code Prefix: NYT66-0294RH

**General Description:** A manufactured fiber in which the fiber-forming

substance is a long-chain synthetic polyamide in which less than 85% of the amide linkages are

attached directly to two aromatic rings.

Standard Filament Size: 3.0 denier per filament (dpf)

Standard Cut Lengths: 1/8", 1/4", 1/2", 3/4", and 1"

(3mm, 6mm, 13mm, 19mm, and 26mm) Other lengths available upon request.

**Shrinkage, Hot Air, 177C:** ~3.4 to 6.0%

Breaking Tenacity: ~9.0 g/den

**Initial Moisture Content: <6.0%** 

Average Moisture Regain of Nylon: 3.5 to 5.0%

Specific Gravity: 1.14 g/cm<sup>3</sup>

Effect of Heat: Sticks at 445°F. Melts at 480 to 500°F. Yellows

slightly at 300°F when held for 5 hours.

Chemical Reactivity: Degraded by hot, concentrated acids and alkalis.

Packaging: Fiber is packaged in corrugated boxes with

polyethylene liners. Custom packaging available

upon request.

The above information is provided to describe typical values and does not constitute a product specification. MiniFIBERS warrants that for each Product sold, such Product will meet the standard specifications provided for that Product and will be of a quality consistent with the standard specifications. This is the sole warranty given with respect to the Product, and is given expressly in lieu of any other warranties, expressed or implied, including without limitation any implied or general warranty of merchantability or of fitness for a particular purpose. It is expressly understood that any technical advice or assistance that may be provided by MiniFIBERS is rendered without compensation, and MiniFIBERS assumes no obligation or liability for such advice or assistance given, or for results obtained.

Doc: PI-TDS\_Nylon-66-Fibers-Bright-High-Tenacity\_0294RH