

MINIFIBERS, INC.

Technical Data Sheet



FIQUE FIBERS

Fiber Diameter (um)	Tensile Strength (MPa)	Tensile Modulus (GPa)	Density (g/cm ³)	Specific Modulus (GPa/g/cm ³)	Moisture (%)	Applications	Raw Material Origin
160-400	130-570	8.2-9.1	1.47	6	6-12	Structural composites, packaging, geotextiles, concrete/shot crete	Lithuania



E2Eco® is a registered trademark of MiniFibers, Inc.

The above information is provided to describe typical values and does not constitute a product specification. It is expressly understood that any technical advice or assistance that may be provided by MiniFIBERS is rendered without compensation, and MiniFIBERS assumes no obligation or liability for such advice or assistance given, or for results obtained.