



## Technical Data Sheet

### PHYSICAL PROPERTIES SYNTHETIC PULP

PRODUCT CODE	AVERAGE FIBER LENGTH (mm)	FIBER DIAMETER (microns)	SURFACE AREA (m <sup>2</sup> /gm) (measured by gas absorption)	AVERAGE CSF (cc)	DRAINAGE FACTOR (sec/gm)	AVERAGE MOISTURE %	DENSITY	MELTING POINT	MELT INDEX (g/10 min)	DRY WEIGHT PER BALE (lbs)
ESS2	~0.6	5	12	550	2.0	47	0.96	275°F(135°C)	60	248.02
ESS5	~0.1	5	12	570	1.9	50	"	"	420	228.18
EST8	0.43~0.67	5	10	540	2.5	59	"	"	7	188.49
E380	0.41~0.57	15	8	720	0.3	39	"	"	22	287.70
E400	0.46~0.68	15	8	580	2.0	63	"	"	7	168.65
E620	0.51~0.79	15	8	340	6.0	64	"	"	3	168.65
E699	0.59~0.83	22	7	685	0.8	59	"	"	7	188.49
E790	0.74~1.08	20	8	680	0.5	50	"	"	7	228.18
E990	0.79~1.21	20	8	725	0.4	50	"	"	7	228.18
AU690	0.59~0.91	-	-	680	-	52	0.93	248°F(123°C)	<1	178.57
NL491	0.46~0.74	26	3.4	720	0.4	55	0.94	212°F(100°C)	2.5	168.65

Fybrel® is a trademark of Mitsui Chemicals, Inc.

The above information is provided to describe typical values and does not constitute a product specification. MiniFIBERS warrants that for each Product sold, such Product will meet the standard specifications provided for that Product and will be of a quality consistent with the standard specifications. This is the sole warranty given with respect to the Product, and is given expressly in lieu of any other warranties, expressed or implied, including without limitation any implied or general warranty of merchantability or of fitness for a particular purpose. It is expressly understood that any technical advice or assistance that may be provided by MiniFIBERS is rendered without compensation, and MiniFIBERS assumes no obligation or liability for such advice or assistance given, or for results obtained.

***MINIFIBERS, INC.***